

Product Information

HIGH GLOSS DRESSING

Description

Tile Star High Gloss Dressing gives the look of a glazed surface to all unglazed tiles. It protects against stains caused by dirt, food, and household products.

Recommended for use on quarry, slate, saltillo and other unglazed tile.

WARNING: WET FLOORS ARE SLIPPERY.

Use proper caution anytime floors are wet. This product is not recommended for exterior use or use on interior floors that are subject to standing water or wet conditions.

Directions

PREPARATION: Clean floor thoroughly to remove all surface soil and stains. Rinse well and allow to dry. If no sealer is in place, apply two coats of Tile Star Matte Finish Sealer.

APPLICATION: Apply a moderately thin coat of dressing with a clean lamb's wool applicator or a cotton string mop. Minimize the amount of dressing in the grout lines. Allow to dry for at least 45 minutes, then apply a second coat in the same manner.

Two coats will usually be sufficient to produce an even gloss. If a higher gloss is desired, a third coat can be applied at this time. It is important that the surface to be covered is completely clean, free of any wax finish and thoroughly dry.

For a new tile installation, it is recommended that fresh grout be allowed to cure 28 days to allow evaporation of moisture before coating.

NOTE: Floors installed with thin set mortar must be allowed to cure for four weeks after grouting before they can be sealed. Floors installed with epoxy mortar must be allowed to cure for 48 hours after grouting.

MAINTENANCE: Clean floor as needed using Tile Star Neutral Cleaner.

RECOAT: Apply additional light coats as desired to clean, dry floors. Avoid excessive buildup by periodic stripping.

CAUTION: Contains polymer emulsions. Undiluted product may cause eye irritation. Avoid contact with eyes. Do not take internally.

FIRST AID: In case of contact, flush eyes with plenty of water for 15 minutes. If irritation persists, see a doctor.

KEEP OUT OF REACH OF CHILDREN KEEP FROM FREEZING

Specifications

Type product	Zinc crosslinked acrylic polymer
pH	9 ± 0.5
Appearance	Opaque white
Percent solids	20 ± 0.5
Weight per gallon	8.65 lbs.
Freeze/thaw stability	Passes 3 cycles
Resistance to abrasion	Excellent
Drying time (normal conditions)	20 - 30 minutes
Washability	Excellent
Coverage	800 - 1000 sq. ft. per gallon